

Carbon Enterprises Ltd
10 Orchard Way
Esher
Surrey KT10 9DY
United Kingdom

Tel: (44) 01322 860590
 Fax: (44) 01322 860586

E Mail: ce@carbonenterprises.co.uk
www.carbonenterprises.co.uk

Calu L-03

Specification		Typical
Calcination		Low
Al ₂ O ₃	%	>70
Sieve Analysis residue on + 90 µm	%	>0.1
+ 63 µm	%	0.1-0.29
D10 Cilas	µm	0.9
D50 Cilas	µm	7.8
D90 Cilas	µm	38
Oil absorption	%	30 – 40
Primary crystal size	µm	<1
Loose bulk density	g/l	500 – 800
Surface area	m ² /g	10 – 17
Specific gravity	g/cm ³	3.9
Cut		2
Polishing effect		9

Chemical Analysis		Typical
Al ₂ O ₃	%	99
Na ₂ O	%	0.42
Fe ₂ O ₃	%	0.03
SiO ₂	%	0.02

***All sales are made strictly in accordance with Carbon Enterprises
 Terms and Conditions of which are available on request***