

Carbon Enterprises Ltd
10 Orchard Way
Esher
Surrey KT10 9DY
United Kingdom

Tel: (44) 01322 860590
 Fax: (44) 01322 860586

E Mail: ce@carbonenterprises.co.uk
www.carbonenterprises.co.uk

Calu L-04

Specification		Typical
Calcination		Low
Al ₂ O ₃	%	>70
Sieve Analysis residue on + 56 µm	%	0.11
+ 40 µm	%	>2.9
D10 Cilas (µm)	µm	0.69
D50 Cilas (µm)	µm	4
D90 Cilas (µm)	µm	21
Oil absorption	%	32 – 40
Primary crystal size	µm	<1
Loose bulk density	g/l	420 – 600
Surface area	m ² /g	10 – 18
Specific gravity	g/cm ³	3.9
Cut		2
Polishing effect		9

Chemical Analysis		Typical
Al ₂ O ₃	%	99
Na ₂ O	%	0.42
Fe ₂ O ₃	%	0.021
SiO ₂	%	0.01

***All sales are made strictly in accordance with Carbon Enterprises
 Terms and Conditions of which are available on request***