

Carbon Enterprises Ltd
10 Orchard Way
Esher
Surrey KT10 9DY
United Kingdom

Tel: (44) 01322 860590
 Fax: (44) 01322 860586

E Mail: ce@carbonenterprises.co.uk
www.carbonenterprises.co.uk

Calu L-06

Specification		Typical
Calcination		Low
Al ₂ O ₃	%	>71
Sieve Analysis residue on + 56 µm	%	Max 0.48
+ 40 µm	%	0.11 – 5
D10 Cilas (µm)	µm	0.2
D50 Cilas (µm)	µm	14
D90 Cilas (µm)	µm	51
Oil absorption	%	34 – 43
Primary crystal size	µm	<1
Loose bulk density	g/l	550 – 800
Surface area	m ² /g	10 – 17
Cut		2
Polishing effect		9

Chemical Analysis		Typical
Na ₂ O	%	0.4
Fe ₂ O ₃	%	0.019
SiO ₂	%	0.01

***All sales are made strictly in accordance with Carbon Enterprises
 Terms and Conditions of which are available on request***