

◆ *Carbon Enterprises Ltd.*

*10 Orchard Way
Esher
Surrey
KT10 9DY
United Kingdom*

*Tel: 44 (0) 1372 800 481
Fx: 44 (0) 1372 467 043*

*e-mail: ce@carbonenterprises.co.uk
web site: www.carbonenterprises.co.uk*

MS 94S SLURRY TYPICAL SPECIFICATION

SiO ₂	93.65%
AL ₂ O ₃	0.28%
Fe ₂ O ₃	1.07%
MgO	1.02%
CaO	0.1%
C	1.59%
Na ₂ O	0.50%
H ₂ O	0.38%
K ₂ O	1.68%
LOI	2.03%

Specific gravity (dry)	2.1 – 2.4
Bulk density	1400 kg/m ³
Surface area	21 – 23 m ² /gm
Particle size	96.4% < 15 micron
Dry mass variation	50% +/- 2%
pH	5.0 – 5.5

NOTE: MS 93 slurry is a stable product however if it not agitated or circulated for some time gravity separation will occur.

Do not expose the product to temperatures below freezing during storage or use.