

◆ *Carbon Enterprises Ltd.*

*10 Orchard Way Tel: 44 (0) 1372 475 945
Esher
Surrey
KT10 9DY
United Kingdom*

*email: ce@carbonenterprises.co.uk
web: www.carbonenterprises.co.uk*

LK 35 TYPICAL SPECIFICATION

PRODUCT DATA

Calcination		Low
D10 Cilas	micron	0.5 - 2.5
D50 Cilas	micron	20 - 36
D90 Cilas	micron	65 85
Oil absorbtion	%	32 - 47
Loose bulk density	g/l	700 - 1000
Specific surface (BET)	m ² /g	9 - 17
Cut		3
Polish		8

CHEMICAL ANALYSIS

Na ₂ O	%	0.37
Fe ₂ O ₃	%	0.015
SiO ₂	%	0.007
Al ₂ O ₃	%	99
CaO	%	0.015

Tariff 2818.2000 CAS 1344-28-1