

◆ *Carbon Enterprises Ltd.*

10 Orchard Way Tel: 44 (0) 1372 475 945
Esher
Surrey
KT10 9DY
United Kingdom

email: ce@carbonenterprises.co.uk
web: www.carbonenterprises.co.uk

LK 9 TYPICAL SPECIFICATION

PRODUCT DATA

Calcination		Low
D10 Cilas	micron	
D50 Cilas	micron	6 - 12
D90 Cilas	micron	35 - 55
Oil absorbtion	%	25 - 40
Loose bulk density	g/l	500 - 800
Surface area (BET)	m2g	9 - 17
Cut		2
Polishing effect		9

CHEMICAL ANALYSIS

Na ₂ O ₃	%	0.37
Fe ₂ O ₃	%	0.015
SiO ₂	%	0.007
Al ₂ O ₃	%	99
CaO	%	0.015

Tariff 2818.2000 CAS 1344-28-1