

◆ *Carbon Enterprises Ltd.*

10 Orchard Way Tel: 44 (0) 1372 475 945
Esher
Surrey
KT10 9DY
United Kingdom

email: ce@carbonenterprises.co.uk
web: www.carbonenterprises.co.uk

LK 6 TYPICAL SPECIFICATION

PRODUCT DATA

| | | |
|------------------------|-------------------|-----------|
| Calcination | | Low |
| D10 Cilas | µm | |
| D50 Cilas | µm | 3 - 7 |
| D90 Cilas | µm | 15 - 35 |
| Oil absorbtion | % | 30 - 40 |
| Loose bulk density | g/l | 500 - 800 |
| Specific surface (BET) | m ² /g | 10 - 17 |
| Cut | | 2 |
| Polish | | 9 |

CHEMICAL ANALYSIS

| | | |
|--------------------------------|---|-------|
| Na ₂ O | % | 0.37 |
| Fe ₂ O ₃ | % | 0.015 |
| SiO ₂ | % | 0.01 |
| Al ₂ O ₃ | % | 99 |
| CaO | % | 0.015 |

Tariff 2818.2000 CAS 1344-28-1